



# PAVSEEL®

## For in-situ binding of jointing sand in block paving.

**Anglo Pavseel Solvent Free** has proved to be the ultimate answer to the problems associated with stabilising the essential jointing sand and helping to protect the integrity of block paving in some of the world's most demanding applications.

- **Reduces maintenance costs**  
**Resists jointing sand removal**
- **Withstands vacuum cleaning**  
**Strengthens pavements**
- **Inhibits water/fuel penetration**  
**Inhibits weed growth**
- **Long performance life**  
**Easy to apply**
- **Stable under normal UV radiation**

Anglo Pavseel Solvent Free is ideal for use on footpaths, pedestrian precincts, domestic driveways, office car parks, retail parks and highways.



# PROFESSIONAL QUALITY

# **PRODUCT INFORMATION**

## **ANGLO PAVSEEL®**

### **APPEARANCE**

Opaque on application which clears once cured. Application will result in a slight darkening of the blocks. We recommend inconspicuous testing on colour-crucial areas.

### **AVAILABILITY**

Available in 5 litre and 25 litre containers.

### **COVERAGE**

Typical coverage is approximately 10m<sup>2</sup> per 5 litres, depending on the porosity of the pavers, block size and joint width.

### **STORAGE**

Keep in a cool place (between 10°C and 30°C). Do not allow to freeze.

#### **Surface Preparation**

Surfaces to be treated must be dry, free from grease, oil, dirt and previous coatings. Joints should be filled or topped up to the bottom of the chamfer with clean, dry compacted sand of the correct specification.

### **APPLICATION**

Ground temperatures should be between 10°C and 30°C. Apply only when the blocks, jointing sand and bedding sand are dry and when rain is not expected for at least 24 hours. Only one application is required. Pour directly from the container or apply with a watering can fitted with a rose. Low pressure spray systems can also be used. Do not flush out the jointing sand. Work in areas of approximately 5m<sup>2</sup>, distributing the liquid evenly with a foam rubber squeegee. Ensure that the joints are completely filled with liquid and that the joints and pavers have absorbed as much solution as they can. Use the squeegee to remove all unabsorbed liquid from the surface of the pavers.

Please Note: the product must not be allowed to pond on the surface of the pavers or create a surface film. Any unabsorbed material must be pushed away using the squeegee. Dry conditions at the time of application are important since damp or rain in contact with uncured Anglo Pavseel can cause the product to dry with a whitish 'bloom'. This effect will be exaggerated if any surplus of solution is not removed from the blocks with the squeegee at the time of application.

### **CURING TIME**

Surfaces treated with Anglo Pavseel Solvent Free can normally be re-opened to foot traffic within 12 - 24 hours. Protect from rain and frost while curing. A warm dry wind will speed curing time.

### **LIMITATIONS**

Only suitable for application to bare, unsealed block pavers.

### **SAFETY**

Anglo Pavseel must not be flushed down drains, storm drains or allowed to enter open water courses. All product labels provide general safety information. Material Safety Data Sheets are available. Food products must be removed from the area during application and cure.

### **ORDERING**

Available from stockists throughout the UK. All Anglo products are sold subject to the Company's Standard Conditions of Sale. The Company and its representatives are often asked to comment on potential uses of Anglo products which differ from those described in the Company's data sheets. Whilst in such cases the Company and its representatives will always try to offer helpful and constructive advice, the Company cannot be held responsible for the results of such uses unless they are specifically confirmed in writing by the Company. All information is based on results gained from experience and testing and is believed to be accurate, but it is given without acceptance of liability for loss or damage attributable to reliance thereon as conditions of use lie outside our control.

**WWW.ANGLOBUILD.CO.UK**

**Rust-Oleum UK Ltd.**

Unit 6, Spitfire Close, Coventry Business Park, Coventry, CV5 6UR, United Kingdom

T +44 (0)2476 717 329 F +44 (0)2476 718 930

info.uk@ro-m.com www.ro-m.com