



# ROOF REPAIR COMPOUND

**A unique blend of rubberised bitumen and tough fibre reinforcement that provides a flexible and very durable thick black weatherproofing seal to all roofs.**



**Anglo Roof Repair Compound** avoids the need for costly re-roofing and is ideal for repairs to asbestos, corrugated iron, concrete, tiled and felted roofs and leaking gutters.

- **Highest quality thick, reinforced brushable rubberised bitumen**
- **Emergency repairs can be made in pouring rain**
- **Will not sag or flow under summer sun**



## PROFESSIONAL QUALITY

# **PRODUCT INFORMATION**

## **COMPOSITION**

A blend of rubber, polymer modified bitumen and special fibre reinforcement

## **AVAILABILITY**

5kg tins. Reinforcement scrim is also available.

## **PROPERTIES**

Exceptional weatherproofing properties, will not sag or flow under very high temperatures. Actively displaces water. High build and flexible.

## **SURFACE PREPARATION**

Surfaces should preferably be as dry as possible. Emergency patch repairs can however be successfully completed to surfaces with running water. Remove all loose material and dirt. A wire brush should be used to remove all traces of moss etc., and Anglo Fungicidal Wash used. Very porous, dry surfaces should be primed with Anglo Roof Repair Compound diluted with 25% white spirit.

## **APPLICATION**

Anglo Roof Repair Compound should be applied generously by brush at the rate of 1m<sup>2</sup> per kilo. If a second coat is required it should be applied at right angles to the first coat. Do not brush out to a thin film. Cracks, splits, holes and leaks around roof sheet overlaps should be treated in the following manner: Apply a generous coat of Anglo Roof Repair Compound and immediately bed in a strip of Scrim or similar, cut to a suitable size.

Apply a further coat of Anglo Roof Repair Compound over the Scrim using a stippling action and leave to set. Deep pits and cracks in flat concrete roofs etc., can be filled with a mortar consisting of dry sand and Anglo Roof Repair Compound. Pits or cracks should be primed first with Anglo Roof Repair Compound before trowelling in the sand/Roof Repair Compound mix.

## **COVERAGE**

1m<sup>2</sup> per kilo

## **CURING TIME**

A surface skin will form after approximately 24 hours. Curing will only commence once any surface water has evaporated.

## **CLEANING OF APPLICATORS**

Anglo Multi-Purpose Degreaser.

## **STORAGE**

Store away from sources of heat or ignition.

## **SAFETY**

All product labels provide general safety information.

Material Safety Data Sheets are available.

Keep away from children and all animals during the cure period.

## **LIMITATIONS**

Anglo Roof Repair Compound is not suitable for coating bare wooden substrates in order to form a waterproofing seal.

Entrapped moisture on porous surfaces may cause blistering in warm weather or spalling at low temperatures. Only limited emergency patch repairs should therefore be made to porous surfaces while wet.

## **ORDERING**

Available from stockists throughout the U.K. and from distributors worldwide. All Anglo products are sold subject to the Company's Standard Conditions of Sale.

The Company and its representatives are often asked to comment on potential uses of Anglo products which differ from those described in the Company's data sheets. Whilst in such cases the Company and its representatives will always try to offer helpful and constructive advice, the Company cannot be held responsible for the results of such uses unless they are specifically confirmed in writing by Anglo.

All information is based on results gained from experience and tests and is believed to be accurate, but is given without acceptance of liability for loss or damage attributable to reliance thereon as conditions of use lie outside our control.

**WWW.ANGLOBUILD.CO.UK**

**Rust-Oleum UK Ltd.**

Unit 6, Spitfire Close, Coventry Business Park, Coventry, CV5 6UR, United Kingdom

T +44 (0)2476 717 329 F +44 (0)2476 718 930

info.uk@ro-m.com www.ro-m.com